

Technical Data Sheet

Indostov 1090Alu

Hi Sparkles Stoving Primer

Product Description

It is a single component stoving coating, specially designed to be used as primer coat under flamboyant finishes to give the desired flamboyant look. It contains high volume of sparkle aluminium pigments.

Recommended Use

Indostov 1090Alu High Sparkles can either be directly sprayed over phosphate treated steel or can be sprayed over primer coated/ ED coated substance. It is recommended to be used in OEM, Automobile Industries, Bi Cycle, Two/ Four Wheelers, Electric Vehicles Industries and for other sheet Metal fabrication industries.

Physical Data

Colour	: Metallic Aluminium
Finish	: Satin
Stoving Schedule	: 135°C±5°C for 30 mins
Supply Weight (Kg/ Ltr)	: 1.05±0.05
Flash Point	: 26° C
Supply Viscosity (at 30°C temperature)	: 60 ± 10 Seconds @ F-4 Cup
Shelf Life	: 6 months

Film Thickness

Recommended film thickness per coat

Dry Film Thickness	: 30-40µ in single coat
Wet Film Thickness	: 75-100µ in single coat
Theoretical Coverage Rate	: 12.50 sq.mt / lit at recommended DFT of 30µ

Surface Preparation

All surfaces to be coated should be clean, absolutely dry and oil or moisture free before painting application. Oil and grease should be removed by solvent cleaning.

Automotive System: Indostov 1090Alu primer can either be directly sprayed over phosphate treated steel or can be coated over ED coated substrate. It is highly recommended undercoat for Flamboyant finish and suitable to be used in wet-on-wet electrostatic spray coating system.

Primed Surface: Indostov 1090Alu can be applied over anti corrosive primed surface. For final smooth finish, proper sanding of already coated primer is recommended. Existing system should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.

Application Data

Application Method	: Electrostatic or Conventional Spray/ Pressure Feed
Application Viscosity	: 20 ± 02 Seconds @ F-4 Cup at 30°C
Thinner and Cleaner	: Indokote Thinner (IK.1707)
Inter Coat Time	: 05–10 Minutes (depending on booth temperature)
Flash Off Time	: 10–15 Minutes (depending on booth temperature)
Recommended Booth Conditions	: Temperature: 25–30°C, Relative Humidity: 55–70 %

Working Precautions: Material should not be allowed to remain in pipeline, hoses, gun or spray equipment. Thoroughly flush all equipment with IK.1702 thinner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages, the work should recommences with freshly mixed units.

Maintenance: Clean all equipment immediately after use with IK.1702 thinner. It is good working practice to periodically flush out spray equipment during the course of the working day. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

Product Characteristics

Cross Hatch (1mm squares)	: 100/100
Gasoline Resistance (After 12 Hours of Stoving)	: Upto 8 Hours (In full system with top coat)
Pencil Hardness	: Passes H Grade
Salt Spray	: Passes 96 Hours (Full System)
Flexibility	: Passes Conical Mandrel
MEK Test	: Passes 10 rubs (In full system with top coat)

Product Features

The gloss level and surface finish are dependent on paint application method. Whenever possible application should be done with one method only. The best results in terms of gloss and appearance will always be obtained by spray application.

This product must only be thinned using the recommended thinner. The use of alternative thinners, might contains alcohols, can severely affect the curing mechanism of the coating. Indostov 1090Alu should be applied at controlled environment of paint shop and at least 3°C temperatures above dew point.

It may be necessary to apply multiple coats to achieve the total specified system dry film thickness. The ability to apply Indostov 1090Alu in one coat will be affected by the temperature of the substrate. At higher steel temperatures, lower film builds and thin coats are likely to be achieved.

Storage

This is solvent based coating and the containers should be kept in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed.

Precaution

This product is for professional use only. The paint applicators should be trained, experienced and have the capability and equipment to mix and apply the coatings correctly as instructed. Applicators should use appropriate protection equipment when using this product.

This is solvent based product and should be use under well ventilated conditions. Do not inhale spray mist. Skin contact should be avoided. In case of spillage on the skin, it should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water.

Limitation of Liability

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. Our products are often used under conditions beyond INDOKOTE's control. INDOKOTE cannot guarantee anything but the quality of the product itself. No liabilities can be derived from this fact for individual cases. This issue replaces all previous versions – Printed in India.

INDÖKÖTE INDUSTRIES PRIVATE LIMITED

Corporate Office: Level 18, One Horizon Center, Golf Course Road, DLF Phase 5, Gurgaon 122002 Haryana INDIA

Phone: +91 124 430 1776, **Fax:** +91 124 668 7778, **Email:** info@indokote.in, **Web:** www.indokote.in