

Technical Data Sheet

Indothane 1067

Acrylic Polyurethane High Protective Finish

Product Description

Two component Acrylic Polyurethane based, Aliphatic Isocyanate cured High Performance, Medium Solid finish to provide excellent Gloss and Gloss retention. Indothane 1067 is highly recommended finish coat in chemical highly corrosive industrial environments.

Recommended Use

This product is recommended as topcoat over Epoxy or PU based anti corrosive primed surface in a wide range of aggressive environments. It is recommended for Refineries, Chemical Plants, Offshore Structures, Power Plants, Petrochemical complexes, Bridges and Heavy Infrastructure Projects. Indothane 1067 has excellent application properties, environmental durability and chemical resistance.

Physical Data

Colour	: Any IS/ RAL/ Custom Shades
Finish	: Glossy (70-85GU)
Soild by Volume	: 50 ± 2%
Supply Weight (Kg/ Ltr)	: 1.10±0.05
Flash Point	: 26° C
Dry Heat Resistance	: Intermittent : 120°C, Continuous: 100°C
Shelf Life	: 12 months

Film Thickness

Recommended film thickness per coat

Dry Film Thickness	: 40-60μ in single coat
Wet Film Thickness	: 80-120μ in single coat
Therotical Coverage Rate	: 12.50 sq.mt / lit at recommended DFT of 40μ

Surface Preparation

All surfaces to be coated should be clean, absolutely dry and oil or moisture free before painting application. Oil and grease should be removed by solvent cleaning.

Primed Surface: Indothane 1067 should be always be applied over anti corrosive primed surface. For final smooth finish, proper sanding of already coated primer is recommended. Existing system should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.

Maintenance: Area of damage or rework etc should be prepared as per specified standards, either by power tool cleaning or other means. A patch primer should be applied before application of Indothane 1067 for desired performance of the product.

Application Data

Application Method	: Conventional Spray/ Airless Spray/Brush/ Roller
Mixing Ratio	: 4 Part (Base) : 1 Part (Hardener)
Pot Life	: Three Hours at 30°C
Thinner and Cleaner	: Indothane PU Thinner (IK.1705)
Airless Nozzle Orifice	: 0.33 - 0.45mm
Nozzle Pressure	: 155 kg/cm ² or 2200 psi

Working Precautions: Material should not be allowed to remain in pipeline, hoses, gun or spray equipment. Thoroughly flush all equipment with IK.1702 thinner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages, the work should recommences with freshly mixed units.

Maintenance: Clean all equipment immediately after use with IK.1702 thinner. It is good working practice to periodically flush out spray equipment during the course of the working day. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.

Drying Characteristics

Surface Dry	: 60 mins
Touch Dry (to Handle)	: 3 Hours
Hard Dry	: 24 Hours
Overcoating Interval	: Minimum 3 Hours

Drying and curing times are determined at 30°C under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Compatibility

Previous Coating	: Epoxy, Epoxy MIO, Epoxy Mastic, Epoxy Zinc Rich, Polyurethane
Subsequent Coating	: Self, Indothane 1067HS

Product Features

The gloss level and surface finish are dependent on paint application method. Whenever possible application should be done with one method only. The best results in terms of gloss and appearance will always be obtained by air spray application.

When overcoating after aging, coating should be fully cleaned to remove all surface contamination such as oil, grease, salts, traffic fumes etc.

This product must only be thinned using the recommended thinner. The use of alternative thinners, might contains alcohols, can severely affect the curing mechanism of the coating. Indothane 1067 should be applied at least 3°C temperatures above dew point. During winters or at low temperature areas, condensation occurring during or immediately after application may result in a matt finish and an inferior film.

When applying Indothane 1067 by brush or roller, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.

The ability to apply Indothane 1067 in one coat will be affected by the temperature of the substrate. At higher steel temperatures, lower film builds and thinner coats are likely to be achieved.

Storage

This is solvent based coating and the containers should be kept in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed.

Precaution

This product is for professional use only. The paint applicators should be trained, experienced and have the capability and equipment to mix and apply the coatings correctly as instructed. Applicators should use appropriate protection equipment when using this product.

This is solvent based product and should be use under well ventilated conditions. Do not inhale spray mist. Skin contact should be avoided. In case of spillage on the skin, it should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water.

Limitation of Liability

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. Our products are often used under conditions beyond INDOKOTE's control. INDOKOTE cannot guarantee anything but the quality of the product itself. No liabilities can be derived from this fact for individual cases. This issue replaces all previous versions – Printed in India.

INDÖKÖTE INDUSTRIES PRIVATE LIMITED

Corporate Office: Level 18, One Horizon Center, Golf Course Road, DLF Phase 5, Gurgaon 122002 Haryana INDIA

Phone: +91 124 430 1776, **Fax:** +91 124 668 7778, **Email:** info@indokote.in, **Web:** www.indokote.in